

<b>Technical Specification for 60*60 SOLUBLE SALT</b>		
<b><u>SR NO</u></b>	<b><u>CHARACTERISTICS</u></b>	<b><u>values</u></b>
-	<b>DIMENSION &amp; SURFACE QUALITY</b>	-
1	Deviation in Length & Width	+ / - 0.1 %
2	Deviation in Thickness	+ / - 2.0 %
3	straightness of Sides	+ / - 0.1 %
4	Rectangularity	+ / - 0.1 %
5	Surface Flatness	+ / - 0.2 %
6	Color Differences	No Change
7	Surface Coating	Nano Polished
8	Thickness	8 mm
	<b>PHYSICAL PROPERTIES</b>	
1	Water Absorption	< 0.08%
2	Flexural Strength	> 30 N / mm <sup>2</sup>
3	Mohs Hardness	7 Mohs
4	Flexural Breaking Strength	2350 N
5	Bulk Density ( gm / cc )	2.35 gm/cc
6	Glossiness	min 65 % reflection
7	Slip Resistance Coefficient of Friction	> 0.6
8	Deep Abrasion Resistance	Max 145 mm <sup>3</sup>
	<b>CHEMICAL PROPERTIES</b>	
1	Staining Resistance	Resistant
2	Household Chemicals	No Damage
	<b>THERMAL PROPERTIES</b>	
1	Termal Shock Resistance	No Damage
2	Termal Expansion	6 x 10 <sup>-6</sup>
3	Moisture Expansion	Nill



**VARMORA GRANITO PVT. LTD.**

Head Office : B-A, National Highway, At: Dhruva, Tal. Wankaner, Dist. Morbi (Gujarat) India. Tel. : +91-98252 23068, E-mail : info@varmora.com  
 Corporate Office : A-54, 1st Floor, Elite Auto House, Mathurdas Vasantji Road, Andheri - Kurla Road, Andheri (E), Mumbai-400093,  
 Tel. : +91-22-28389790/91/92, Fax : +91-22-28389794, E-mail : mumbai@varmora.com Visit us at : www.varmora.com  
 Office : 5-Savsar plot, Opp. Priyadarshini Complex, Nr. old Bus Stand, Morbi - 363 641, Gujarat, INDIA.

C.I.No. : UJ6914GJ2003PTC043194